

Product Data

Somos[®] NeXt LV Grey

Description

Somos[®] NeXt LV Grey creates tough, ABS-like parts with a high modulus while maintaining a low viscosity for effortless cleaning. Somos[®] NeXt LV Grey has good water resistance and thermal properties. This third generation Somos[®] high impact material focuses on creating quality resins that can produce tough, complex parts.

Applications

Somos[®] NeXt LV Grey produces parts that are more resistant to fracture and cracking than standard SL resins. It is ideal for use in functional testing and low-volume manufacturing applications.

This resin is excellent for functional end-use performance parts, especially snap-fit designs, impellers, connectors, and sporting goods.

TECHNICAL DATA - LIQUID PROPERTIES

Appearance	Opaque Grey
Viscosity	~480 mPas @ 30°C
Density	~1.12 g/cm ³ @ 25°C

TECHNICAL DATA - OPTICAL PROPERTIES

E _c	10.23 mJ/cm ²	[critical exposure]
D _p	5.04 mils	[slope of cure-depth vs. ln (E) curve]
E ₁₀	101.2 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]

TECHNICAL DATA			
Mechanical Properties		Somos® NeXt LV Grey UV Postcure	
ASTM Method	Property Description	Metric	Imperial
D638M	Tensile Modulus	2,970 - 3,285 MPa	431 - 476 ksi
D638M	Tensile Strength at Yield	60 - 66 MPa	8.7 - 9.6 ksi
D638M	Elongation at Break	4.6 - 7.2%	4.6 - 7.2%
D638M	Elongation at Yield	3.0%	3.0%
D790M	Flexural Stress at 5% Strain	4.6 - 7.2%	4.6 - 7.2%
D790M	Flexural Modulus	1,843 - 2,017 MPa	267 - 292 ksi
D256A	Izod Impact (Notched)	0.30 - 0.35 J/cm	0.56 - 0.66 ft-lb/in
D2240	Hardness (Shore D)	84	84
D570-98	Water Absorption	0.36 - 0.40%	0.36 - 0.40%

TECHNICAL DATA			
Thermal/Electrical Properties		Somos® NeXt LV Grey UV Postcure	
ASTM Method	Property Description	Metric	Imperial
E831-06	C.T.E. before Tg (~44°C)	74.3 - 80.5 µm/m°C	41.2 - 44.7 µin/in°F
E831-06	C.T.E. after Tg (~44°C)	218 - 236 µm/m°C	121.1 - 131.1 µin/in°F
D150-98	Dielectric Constant and Dissipation Factor 1 kHz	k' = 3.75, D = 0.02	k' = 3.75, D = 0.02
D149-97a	Dielectric Strength	21.6 - 23.4 kV/mm	549 - 594 V/mil
E1545-05A	Tg	40 - 48°C	104 - 118°F
D648-07B	Deflection Temperature (0.46 MPa)	53 - 57°C	127 - 135°F
D648-07B	Deflection Temperature (1.82 MPa)	49 - 57°C	120 - 135°F

DSM Functional Materials
Somos® Materials Group

in North America

1122 St. Charles Street
Elgin, Illinois 60120
USA
Phone: +1.847.697.0400

in Europe

Slachthuisweg 30
3150 XN Hoek van Holland
The Netherlands
Phone: +31.174.315.391

in China

476 Li Bing Road
Zhangjiang Hi-Tech Park
Pudong New Area
Shanghai 201203, China
Phone: +86.21.6141.8064

Visit us online at www.dsm.com/somos

NOTICE : Somos® is a registered trademark of Royal DSM N.V. Somos® is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties which may be implied including warranties of merchantability and/or fitness for a particular purpose DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice. © 2012 DSM IP ASSESTS B.V. All rights reserved.